

Klüberplus SK 11-299

Lubricating wax for chains



Benefits for your application

- “Quasi-dry”, non-tacky lubricant film
- Wear protection
- High corrosion protection
- Good adhesion
- Excellent water resistance

Description

Klüberplus SK 11-299 is a lubricating wax based on wax-like hydrocarbons and a synthetic hydrocarbon oil. It protects reliably against wear, shows excellent adhesion and is extremely resistant to water, thus providing excellent corrosion protection also when in contact with water. Once applied to the component surface, the lubricant leaves a “quasi-dry” non-tacky lubricant film.

Application

Klüberplus SK 11-299 was especially developed for the initial lubrication of steel chains. It is particularly suitable for chains exposed to dust, dirt, lint or water. This product makes it possible to lubricate chains which, due to the operating conditions, could not be lubricated in the past. Klüberplus SK 11-299 ensures long-term and in some cases even lifetime lubrication in transport, drive and control chains subject to low loads, which operate at a chain temperature of 60 °C maximum and under moderate ambient conditions.

In the low-temperature range, higher starting torques are possible after longer periods of chain standstill. Shorter relubrication intervals may be required at temperatures above 80 °C, depending on the chain load and speed.

Application notes

Klüberplus SK 11-299 has been especially designed for the initial lubrication of chains by hot dipping. When applied by hot dipping, we recommend an immersion bath temperature of 90 °C to 100 °C. Chains should remain in the bath until bubbling has stopped. We recommend preheating the components in order to reduce the period in the immersion bath. Excess wax can be blown off with hot air (80 to 90 °C) after the bath.

Chains can be relubricated with any chain lubricant suiting the individual requirements (except for polyalkylene glycol oils).

Material safety data sheets

Material safety data sheets can be requested via our website www.klueber.com. You may also obtain them through your contact person at Klüber Lubrication.

Pack sizes	Klüberplus SK 11-299
Bucket 25 kg	+

Product data	Klüberplus SK 11-299
Article number	012219
Lower service temperature	-40 °C / -40 °F
Upper service temperature	120 °C / 248 °F
Colour space	yellow
Texture	solid
Density at 20 °C	approx. 0.89 g/cm ³



Klüberplus SK 11-299

Lubricating wax for chains

Product data	Klüberplus SK 11-299
Flash point, DIN EN ISO 2592, Cleveland, open-cup apparatus	> 200 °C
Corrosion protection behaviour, DIN EN ISO 6270-2, condensation water in alternating atmosphere, 40 °C, material steel ST 37, corrosion after	>= 20 cycles
Needle penetration of paraffins, DIN ISO 51579, 25 °C	70-100 x 0.1 mm
Water resistance, based on DIN 51807 pt. 01, 5h/60 °C	0 - 60
Drop point, DIN ISO 2176	70-80 °C
Minimum shelf life from the date of manufacture - in a dry, frost-free place and in the unopened original container, approx.	36 months

Klüber Lubrication – your global specialist

Innovative tribological solutions are our passion. Through personal contact and consultation, we help our customers to be successful worldwide, in all industries and markets. With our ambitious technical concepts and experienced, competent staff we have been fulfilling increasingly demanding requirements by manufacturing efficient high-performance lubricants for more than 80 years.

**Klüber Lubrication München SE & Co. KG /
Geisenhausenerstraße 7 / 81379 München / Germany /
phone +49 89 7876-0 / fax +49 89 7876-333.**

The data in this document is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a reader with technical experience. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary field tests with the product selected for a specific application. All data are guide values which depend on the lubricant's composition, the intended use and the application method. The technical values of lubricants change depending on the mechanical, dynamical, chemical and thermal loads, time and pressure. These changes may affect the function of a component. We recommend contacting us to discuss your specific application. If possible we will be pleased to provide a sample for testing on request. Klüber products are continually improved. Therefore, Klüber Lubrication reserves the right to change all the technical data in this document at any time without notice.

Publisher and Copyright: Klüber Lubrication München SE & Co. KG. Reprints, total or in part, are permitted only prior consultation with Klüber Lubrication München SE & Co. KG and if source is indicated and voucher copy is forwarded.